

**ÇALIŞMA
SICAKLIĞI**

-55°C ila 125°C

- Ultra ince duvar yapısı
- Yüksek esneklik
- Halojensiz malzeme
- Alev geciktirici özellik

SARI - YEŞİL MAKARON

Daralma Oranı: 2/1

ÖLÇÜ (mm)	ÜRÜN KODU	DARALMADAN ÖNCE (mm)		DARALMADAN SONRA (mm)		MAKARA UZUNLUĞU (m)
		İÇ ÇAP	CİDAR KALINLIĞI	İÇ ÇAP	CİDAR KALINLIĞI	
2,5	SM-2,5SY	3.0 ± 0.4	≤ 1.30	≤ 1.30	0.36 ± 0.10	200
3,0	SM-3SY	3.5 ± 0.4	≤ 1.50	≤ 1.30	0.38 ± 0.10	200
3,5	SM-3,5SY	4.0 ± 0.4	≤ 1.80	≤ 1.50	0.40 ± 0.10	200
4,5	SM-4,5SY	5.0 ± 0.4	≤ 2.30	≤ 2.30	0.45 ± 0.10	100
5,0	SM-5SY	5.5 ± 0.4	≤ 2.50	≤ 2.50	0.45 ± 0.10	100
6,0	SM-6SY	6.5 ± 0.4	≤ 3.00	≤ 3.00	0.50 ± 0.10	100
7,0	SM-7SY	9.5 ± 0.5	≤ 4.50	≤ 3.50	0.55 ± 0.10	100
9,0	SM-9SY	10.5 ± 0.5	≤ 5.00	≤ 4.50	0.55 ± 0.10	100
12,0	SM-12SY	12.5 ± 0.5	≤ 6.00	≤ 6.00	0.60 ± 0.10	100
13,0	SM-13SY	13.5 ± 0.5	≤ 6.50	≤ 6.50	0.60 ± 0.10	100
16,0	SM-16SY	17.0 ± 0.6	≤ 8.00	≤ 8.00	0.70 ± 0.10	100
20,0	SM-20SY	22.0 ± 0.7	≤ 10.00	≤ 10.00	0.75 ± 0.15	100
25,0	SM-25SY	26.0 ± 0.7	≤ 12.50	≤ 12.50	0.90 ± 0.15	50
30,0	SM-30SY	31.5 ± 0.7	≤ 15.00	≤ 15.00	0.95 ± 0.15	50
35,0	SM-35SY	36.5 ± 0.7	≤ 17.50	≤ 17.50	0.95 ± 0.15	50
40,0	SM-40SY	41.5 ± 0.7	≤ 20.00	≤ 20.00	1.00 ± 0.20	50
50,0	SM-50SY	51.0 ± 0.7	≤ 25.00	≤ 25.00	1.00 ± 0.20	25
60,0	SM-60SY	≥ 60	≤ 30.00	≤ 30.00	1.10 ± 0.20	25
70,0	SM-70SY	≥ 70	≤ 35.00	≤ 35.00	1.20 ± 0.20	25
80,0	SM-80SY	≥ 80	≤ 40.00	≤ 40.00	1.30 ± 0.20	25